


Ridgewall Soft Shell Ladies' Jacket FL

NF0A88D4

Product Features:

- 306 g/m²/15 oz lyd WindWall™, 100% recycled post-consumer polyester with non-PFC DWR finish (solid)
- 316 g/m²/15.5 oz lyd WindWall™, 100% polyester with non-PFC DWR finish (heather)
- Highly wind-resistant with wind permeability at less than 10 CFM (0 CFM is 100% windproof)

Ladies' sizes: S-2XL





Available Colours and PMS Colours

Textile fabric colours are subject to dye lot variation and will not be exact match to print pantone reference.



BLACK
Black C



DARK GREY HEATHER
Cool Grey 11C & Cool Grey 8C

Due to the nature of polyester, special care must be taken throughout the decoration process.
The North Face® products may not be resold without embellishment. The North Face® products are not permitted to be shipped to or sold outside of Canada.

NF0A88D4 - Ridgewall Soft Shell Ladies’ Jacket FL

Garment Measurements

Size	S	M	L	XL	2XL
Chest - Half Measure	18 1/4"	19 1/2"	21"	22 3/4"	24 1/2"
Chest - Full Measure	36 1/2"	39"	42"	45 1/2"	49"
Body Length from HPS	25 7/8"	26 1/2"	27 3/8"	28 1/4"	29 1/8"
Sleeve Length - CB	32 1/2"	33"	33 3/4"	34 1/2"	35 1/4"

Finished measurements in inches. Refer to “How to Measure” guide for detailed information on measurement instructions.

Decoration Recommendations

Due to the nature of polyester, special care must be taken throughout the decoration process. Here are some tips to effectively decorate our performance products.

• Garment temperature must not exceed 320°F or 160°C. Exceeding this temperature will cause the fabric to shrink, become wavy or cause dye migration.
• Dryer temperature and belt speeds must be changed accordingly for polyester fabric.
• If flashing these garments, do not exceed 1-2 seconds. Anything longer may damage the fabric as stated above.

SCREEN PRINTING:

These garments require the use of poly inks that cures at a lower temperature. A Dyno Grey base blocker on all colours and a second white base blocker on all dark colours are recommended. Please consult your ink supplier for more information.

• Polyester requires a longer cooling time than cotton. Avoid overlap of garments and screen-print/heat transfer until the garments are cooled. Failure to cool the fabric prior to stacking into a printer’s fold may cause the fabric and applied ink to stick together.

HEAT TRANSFERS:

Poly mark heat transfers need to be created with an anti-migration layer in the design. This process can only be done on white or very light colour shirts. Inks used in printing paper design needs to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.

SUBLIMATION PRINTING:

As noted for the poly mark heat transfers, this process can only be done on white or very light colour shirts. Inks used in printing paper design needs to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.

• If you heat press these garments, you must adjust the time, temperature and pressure. Failure to do so may damage the fabric as stated above.
• A test sample run is recommended, especially if you have a large order or if your printer does not specialize in printing on performance fabrics